


技术参数信息来源EN1817



| EN1817 Characteristics EN1817 要求 | Standard 标准 | Unit 单位 | Requirements 要求 | Average values from production 产品均值 |
|---|-------------------------------------|--------------------|--|--|
| Overall thickness 厚度 | EN 428 | mm | average value $\pm 0,15$ mm 均值 $\pm 0,15$ mm | 3,0 |
| Dimensional stability 尺寸稳定性 | EN 434 | % | $\leq 0,40$ | 0,30 |
| Flexibility ($\varnothing 20$ mm) 柔韧性 (芯棒直径20mm) | EN 435 Met.A 方法A | - | no fissuring 无裂痕 | comply 符合 |
| Hardness 硬度 | ISO 7619 | shore A | ≥ 75 | 85 |
| Residual indentation 残余凹陷 | EN 433 | mm | $\leq 0,20$ | 0,08 |
| Abrasion resistance 耐磨性 | ISO 4649 (Met.A-5N) (方法A, 5N) | mm ³ | ≤ 250 | 170 |
| Colour fastness to artificial light 色牢度 | ISO 105-B02 Met. 3 方法3 | degree | ≥ 6 blue scale 蓝色色标 ≥ 3 grey scale 灰色色标 | comply 符合 |
| Classification 等级 | EN 685 | class | - | 23/34/43 |
| Effect of castor chairs 对滚轮椅的反应 | EN 425 | - | - | suitable for W castors 适合W型滚轮 |
| Characteristics EN14041 EN14041要求 | | | | |
| Fire classification 防火 | GB 8624-2012 | class | - | B1 |
| Dynamic coefficient of friction 动态摩擦系数 | EN 13893 | class | $\geq 0,30$ (DS) | DS 符合 |
| Electrostatic propensity 静电性能 | EN 1815 | kV | - | ≤ 2 (antistatic 抗静电) |
| Thermal resistance 热阻性能 | DIN 52612 | m ² K/W | - | 0,020 |
| Other characteristics 其他要求 | | | | |
| Gas burning toxicity 烟毒性 | DIN 53436 at 350°C | - | - | not toxic 无毒 |
| Anti-slip resistance 防滑性能 | DIN 51130 | ° | BGR 181 | ≥ 6 (R9) |
| Improvement in footfall sound absorption 脚步吸音性能 | ISO 10140-3 | dB | - | up to 10 最高至10分贝 |
| Vertical electrical Resistance (R _v) 电阻性能 (R _v) | EN 1081 Met.A 方法A | ohm | - | $> 10^{10}$ |
| Effect of stains 抗污性 | EN 423 | - | - | resistant* 抗污* |
| Cigarette heat resistance 抗烟头灼烧 | EN 1399 | rating | met.方法 A ≥ 4 met.方法 B ≥ 3 | comply 符合 |
| Environmental characteristics 环保要求 | | | | |
| VOC emissions VOC 排放量 | GB 18586-2001 | - | various | comply 符合 |

* Depending on concentration and time of contact, for specific agent please ask.

* 结果随污渍时间及浓度有所变化，具体试剂请咨询盟多。

Mondo reserves the right to modify the characteristics of the products in any moment.

盟多公司保留随时更改产品特性的权力。

